

Technology of Wood Pellets

<http://www.canadaontheweb.ca> Soft wood waste is the raw material and has to be dried to about 10% moisture content and reduced in size to below 10x10x100mm, before it can be processed into pellets. The core process of the Wood Pelleting Plant comprises of 5 stages: milling, conditioning, pressing, cooling and screening (<http://www.buhlercan.com/woodpelleting.html>).